# PU Moulded T5 -720 Steel

Article code: TBUM000084



General information	
Productgroup	Timing belts, PU Moulded
Industry segment	General industry; Container & packaging; Paper & print
Main product feature	Positive drive, Non-marking, Wear resistant


Belt construction		
Tension member		steel
Material	body	Polyurethane
Surface	tooth side	Polyurethane
	back side	Polyurethane

Characteristics		
Food Grade (FG)	no	
Antistatic (AS)	no	
Oil & Fat resistance	yes	


Technical data						
Tooth	profile		T5			
	pitch		5	mm	0.2	in.
Hardness body material	ISO 868		85A	Shore		
Belt thickness			2.2	mm	0.09	in.
Belt weight			2.4	kg/m²	0.49	lbs/ft²
Coefficient of friction	tooth side to steel	dynamic	0,5			
Operating temperature	continuous	from / to	-30 / 80	°C	-22 / 176	°F
Minimum pulley diameter	A) without counter flexing	number of teeth, t1	10			
		d1	15.05	mm	0.59	in.
		d2	30	mm	1.18	in.
	B) with counter flexing	number of teeth, t1	15			
		d1	23.05	mm	0.91	in.
		d2	30	mm	1.18	in.
Belt width	maximum		300	mm	11.81	in.
Belt length			720	mm	28.35	in.

#### **Reference images**


## Side view



## A) without counter flexing



## B) with counter flexing



### **Fabrication**

This information on the fabrication options is general, please contact Ammeraal Beltech to inquire for the specific fabrication possibilities of the timing belt of your choice.

Cleats welded or mechanically attached, metal teeth, guides welded or glued.

Covers can be welded, glued, coated or vulkanized onto the back side of the timing belt.

Thermoplastic covers can be embossed.

Perforations, lateral and logitudinal slots, lateral and longitudinal profiles.

Tooth profile according to standard: metric ISO 17396 , imperial ISO 5296-1, curvilinear ISO 13050, depending on the belt type.
This sheet contains typical values, which apply to a temperature of approx. 20 °C (68 °F), unless otherwise stated, individual data may differ.
Consult our specialists for further information like technical calculations. Instructions regarding joining, storage & maintenance and tracking & tensioning.

Standard

**Additional Information** 

Because of continuous development, the presented data is subject to alteration. This data replaces that included in previous publications. Ammeraal Beltech excludes any liability for the incorrect use of the above stated information. Subject to the general terms and conditions of sale and delivery, as applied by its operating companies, are all activities performed and services rendered by Ammeraal Beltech.