Technical datasheet

Nonex EM 9/3 0+A42 grey

Article code: SBNO574232



General information	
Product group	Synthetic Belts
Industry segment	Paper & print; Metal
Main product feature	Oil & grease resistant
Indication of use	Slider bed, Rollers, Flat

Belt construction		
Tension layer		polyester, stable
Number of plies		3
Top side	material	Nonex, PVC
	finish	profile, A42 Supergrip wave profile
	color	grey
Bottom side	material	fabric, polyester
	finish	bare fabric
	color	natural

Characteristics		
Food Grade (FG)	no	
Antistatic (AS)	no	
High conductive (HC)	no	
Flame-retardant (FR)	no	
ATEX approval	no	

Technical data						
Hardness	ISO 868	top side	40A	Shore		
Force at 1% elongation (static)	ISO 21181		9	N/mm	51.39	lbs/in.
Thickness	AB method KV.002	total	5.90	mm	0.23	in.
		top cover	2.90	mm	0.11	in.
Weight	AB method KV.004		5.5	kg/m²	1.13	lbs/ft²
Coefficient of friction	bottom against steel	dynamic	0.19			
		static	0.22			
Operating temperature	continuous	from / to	-10 / 90	°C	14 / 194	°F
	short	from / to	-10 / 110	°C	14 / 230	°F
Minimum pulley diameter	flexing		120	mm	4.72	in.
	backflexing		220	mm	8.66	in.
Manufacturing width	standard		2020	mm	79.53	in.
	maximum		2070	mm	81.5	in.

Fabrication

Hot splicing is always preferable. Glueing can only be done when the belt is exposed to normal temperature and the humidity is not excessive. For the working method, consult the splice information and the equipment literature. Apply the recommended splice as indicated in the seperate information.

Additional information

This sheet contains typical values, which apply to a temperature of approx. 20 °C (68 °F), unless otherwise stated, individual data may differ.

We recommend to keep the belt tension to a practical working minimum to maximize the service life of the belt and machine parts.

Always protect belts from sunlight/UV-radiation, avoid temperatures below 10°C and above 40°C, dust and dirt. Store belts in a cool and dry place and if possible in their original packaging.

For details consult 'Storage and handling instructions' or contact our specialist.