

Solicord V-belt TPU 80A Transparent SM FG 6x4

Article code: SCVB000121

General information

| | |
|---------------|----------|
| Product group | SoliCord |
|---------------|----------|

Construction

| | |
|---------------------|-------------|
| Material | TPU |
| (Top)surface finish | smooth |
| Color | transparent |
| Shape | vee |
| Execution | solid |

Characteristics

| | | |
|-----------------|-----|------------------------------|
| Food Grade (FG) | yes | all foodstuff; all foodstuff |
| Antistatic (AS) | no | |
| ATEX approval | no | |

Technical data

| | | | | |
|-------------------------|---------------|-----------|------------------------|--------------|
| Hardness | ISO 868 | | 84A Shore | |
| Recommended pre-tension | | | 7 % | |
| Working tension | | | 15 daN/cm ² | |
| Cross section | | | 0.19 cm ² | |
| Weight | | | 0.023 kg/m | 0 lb/ft |
| Operating temperature | continuous | from / to | -30 / 80 °C | -22 / 176 °F |
| Minimum pulley diameter | | | 40 mm | 1.57 in. |
| Coefficient of friction | against steel | dynamic | 0,65 | |
| | against PE | | 0,35 | |
| | against HDPE | | 0,3 | |
| Manufacturing length | maximum | | 100000 mm | 3937.01 in. |

Fabrication

| | |
|--------------------------|--|
| Recommended splice types | Butt weld |
| Splice equipment | Only use equipment supplied or approved by Ammeraal Beltech. |
| Splicing on site | Always first make a test splice to confirm the right settings and proper pre-heating of the equipment. |

Additional information

This sheet contains typical values, which apply to a temperature of approx. 20 °C (68 °F), unless otherwise stated, individual data may differ.

Keep the belt tension to a practical working minimum for maximum belt and machine life.

Always protect belts from sunlight/UV-radiation, avoid temperatures below 10°C and above 40°C, dust and dirt.