

PVCCON 2R/12 AG27 00/V11 AS

Article code: SBMD000092

General information

Product group	Synthetic Belts
Main product feature	Antistatic

Belt construction

Number of plies		2
Top side	material	PVCCON, PVCCON
	finish	smooth
	color	Apple green
Bottom side	material	Bare fabric, Bare fabric
	finish	profile
	color	natural

Characteristics

Antistatic (AS)	yes
------------------------	-----

Technical data

Hardness	ISO 868	top side	74A Shore	
Force at 1% elongation (static)	ISO 21181		12 N/mm	68.52 lbs/in.
Thickness	AB method KV.002	total	2.70 mm	0.11 in.
		top cover	1.10 mm	0.04 in.
Weight	AB method KV.004		3.4 kg/m ²	0.7 lbs/ft ²
Operating temperature	continuous	from / to	-10 / 70 °C	14 / 158 °F
	short	from / to	-10 / 70 °C	14 / 158 °F
Minimum pulley diameter	flexing		65 mm	2.56 in.
	backflexing		80 mm	3.15 in.
Manufacturing width	standard		3000 mm	118.11 in.

Fabrication

Hot splicing is always preferable. Glueing can only be done when the belt is exposed to normal temperature and the humidity is not excessive.

For the working method, consult the splice information and the equipment literature. Apply the recommended splice as indicated in the separate information.

Additional information

This sheet contains typical values, which apply to a temperature of approx. 20 °C (68 °F), unless otherwise stated, individual data may differ.

We recommend to keep the belt tension to a practical working minimum to maximize the service life of the belt and machine parts.

Always protect belts from sunlight/UV-radiation, avoid temperatures below 10°C and above 40°C, dust and dirt. Store belts in a cool and dry place and if possible in their original packaging.

For details consult 'Storage and handling instructions' or contact our specialist.