Technical datasheet

Ropanyl EM 3/1 00+S21 white AS FG

Article code: SBRY887097



General information					
Product group	Synthetic Belts	Synthetic Belts			
Main product feature	Antistatic, Foodgrade				
Indication of use	Flat, Slider bed				
Belt construction					
Tension layer		polyester, stable			
Number of plies		1			
Top side	material	material Ropanyl, TPU			
	finish	profile, S21 Fine Diamond			
	color	white	white		
Bottom side	material	fabric, PUR			
	finish	impregnated fab	impregnated fabric		
	color	natural			
Characteristics					
Food Grade (FG)	yes				
Antistatic (AS)	yes	ISO 21178			
High conductive (HC)	no				
Flame-retardant (FR)	no				
ATEX approval	no				
Technical data					
Hardness	ISO 868	top side	85A Shore		
Force at 1% elongation (static)	ISO 21181		3 N/mm	17.13 lbs/in.	
Thickness	AB method KV.002	total	1.00 mm	0.04 in.	
		top cover	0.50 mm	0.02 in.	
Weight	AB method KV.004		1 kg/m²	0.2 lbs/ft ²	
Operating temperature	continuous	from / to	-20 / 90 °C	-4 / 194 °F	
	short	from / to	-30 / 110 °C	-22 / 230 °F	

Manufacturing width

Minimum pulley diameter

Fabrication

Hot splicing is always preferable. Glueing can only be done when the belt is exposed to normal temperature and the humidity is not excessive. For the working method, consult the splice information and the equipment literature. Apply the recommended splice as indicated in the seperate information.

8 mm

20 mm

2500 mm

3000 mm

0.31 in.

0.79 in.

98.43 in.

118.11 in.

Additional information

This sheet contains typical values, which apply to a temperature of approx. 20 °C (68 °F), unless otherwise stated, individual data may differ.

We recommend to keep the belt tension to a practical working minimum to maximize the service life of the belt and machine parts.

Always protect belts from sunlight/UV-radiation, avoid temperatures below 10°C and above 40°C, dust and dirt. Store belts in a cool and dry place and if possible in their original packaging.

For details consult 'Storage and handling instructions' or contact our specialist.

flexing

backflexing

standard

maximum

Because of continuous development, the presented data is subject to alteration. This data replaces that included in previous publications. Ammeraal Beltech excludes any liability for the incorrect use of the above stated information. Subject to the general terms and conditions of sale and delivery, as applied by its operating companies, are all activities performed and services rendered by Ammeraal Beltech.