Technical datasheet

Ropanyl EM 10/2 00+02 transparent green AS FG



Article code: SBRY592910

General information							
Product group	Synthetic Belts	Synthetic Belts					
Industry segment	Food: Confectionary & ca	Food: Confectionary & candy, Bakery; Container & packaging					
Main product feature	Antistatic, Foodgrade	Antistatic, Foodgrade					
Indication of use	Slider bed, Rollers, Flat	Slider bed, Rollers, Flat					
Belt construction							
Tension layer		polyester, stable					
Number of plies			2				
Top side	material	Ropanyl, TPU					
	finish	smooth, glossy					
	color	transparent gree	transparent green				
Bottom side	material	Ropanol, PUR					
	finish	impregnated fabr	impregnated fabric				
	color	light green	light green				
Characteristics							
Food Grade (FG)	yes	FDA					
Antistatic (AS)	yes	ISO 21178					
High conductive (HC)	no						
Flame-retardant (FR)	no						
ATEX approval	no						
Technical data							
Hardness	ISO 868	top side	93A	Shore			
Force at 1% elongation (static)	ISO 21181		10	N/mm	57.1	lbs/in.	
Thickness	AB method KV.002	total	1.2	mm	0.05	in.	
		top cover	0.2	mm	0.01	in.	
Weight	AB method KV.004		1.4	kg/m²		lbs/ft ²	
Operating temperature	continuous	from / to	-20 / 90		-4 / 194		
	short	from / to	-30 / 110		-22 / 230		
Minimum pulley diameter	flexing			mm	0.47		
	backflexing		20	mm	0.79	in.	
Manufacturing width	standard		1600	mm	62.99	in.	
	maximum		2000	mm	78.74	in.	
Ended and an							

Fabrication

Hot splicing is always preferable. Glueing can only be done when the belt is exposed to normal temperature and the humidity is not excessive. For the working method, consult the splice information and the equipment literature. Apply the recommended splice as indicated in the seperate information.

Additional information

This sheet contains typical values, which apply to a temperature of approx. 20 °C (68 °F), unless otherwise stated, individual data may differ. We recommend to keep the belt tension to a practical working minimum to maximize the service life of the belt and machine parts.

Always protect belts from sunlight/UV-radiation, avoid temperatures below 10°C and above 40°C, dust and dirt. Store belts in a cool and dry place and if possible in their original packaging.

For details consult 'Storage and handling instructions' or contact our specialist.

Because of continuous development, the presented data is subject to alteration. This data replaces that included in previous publications. Ammeraal Beltech excludes any liability for the incorrect use of the above stated information. Subject to the general terms and conditions of sale and delivery, as applied by its operating companies, are all activities performed and services rendered by Ammeraal Beltech.