Technical datasheet

## Flexam EM05 8/2 00+A88 black CMC

## Article code: SBFL570762



General information							
Product group	Synthetic Belts						
Indication of use	Flat, Rollers, Slider bed						
Belt construction							
Tension layer		polyester, extra s	stable				
Number of plies		2	2				
Top side	material	Flexam, PVC	Flexam, PVC				
	finish	profile, A88 Horse	profile, A88 Horseshoe				
	color	black	black				
Bottom side	material	Ropanol, PUR	Ropanol, PUR				
	finish	impregnated fabr	impregnated fabric				
	color	natural					
Characteristics							
Food Grade (FG)	no						
Antistatic (AS)	no						
High conductive (HC)	no						
Flame-retardant (FR)	no						
ATEX approval	no						
Technical data							
Hardness	ISO 868	top side	50A Shore				
Force at 1% elongation (static)	ISO 21181		8 N/mm	45.68 lbs/in.			
Thickness	AB method KV.002	total	7.20 mm	0.28 in.			
		A	E 40	0.01			

Theress	Ab method RV.002	total	7.20 mm	0.20 III.
		top cover	5.40 mm	0.21 in.
Weight	AB method KV.004		4 kg/m²	0.82 lbs/ft <sup>2</sup>
Operating temperature	continuous	from / to	-15 / 80 °C	5/176 °F
	short	from / to	-15 / 100 °C	5/212 °F
Minimum pulley diameter	flexing		50 mm	1.97 in.
	backflexing		120 mm	4.72 in.
Manufacturing width	standard		1500 mm	59.06 in.
	maximum		1500 mm	59.06 in.

Fabrication

Hot splicing is always preferable. Glueing can only be done when the belt is exposed to normal temperature and the humidity is not excessive. For the working method, consult the splice information and the equipment literature. Apply the recommended splice as indicated in the seperate information.

## Additional information

This sheet contains typical values, which apply to a temperature of approx. 20 °C (68 °F), unless otherwise stated, individual data may differ. We recommend to keep the belt tension to a practical working minimum to maximize the service life of the belt and machine parts.

Always protect belts from sunlight/UV-radiation, avoid temperatures below 10°C and above 40°C, dust and dirt. Store belts in a cool and dry place and if possible in their original packaging.

For details consult 'Storage and handling instructions' or contact our specialist.

Because of continuous development, the presented data is subject to alteration. This data replaces that included in previous publications. Ammeraal Beltech excludes any liability for the incorrect use of the above stated information. Subject to the general terms and conditions of sale and delivery, as applied by its operating companies, are all activities performed and services rendered by Ammeraal Beltech.