Technical datasheet

Flexam EM 16/2 0+08 dark green AS

Article code: SBMD000201



General information	
Product group	Synthetic Belts
Industry segment	General industry
Main product feature	Antistatic
Indication of use	Flat, Rollers, Slider bed

Belt construction		
Tension layer		polyester, stable
Number of plies		3
Top side	material	Flexam, PVC
	finish	smooth, glossy
	color	dark green
Bottom side	material	fabric, polyester
	finish	bare fabric
	color	natural

Characteristics		
Food Grade (FG)	no	
Antistatic (AS)	yes	ISO 21178

Technical data						
Hardness	ISO 868	top side	74A	Shore		
Force at 1% elongation (static)	ISO 21181		16	N/mm	91.36	lbs/in.
Thickness	AB method KV.002	total	3.80	mm	0.15	in.
		top cover	0.8	mm	0.03	in.
Weight	AB method KV.004		4.9	kg/m²	1	lbs/ft²
Operating temperature	continuous	from / to	-10 / 70	°C	14 / 158	°F
	short	from / to	-10 / 70	°C	14 / 158	°F
Minimum pulley diameter	flexing		100	mm	3.94	in.
	backflexing		120	mm	4.72	in.
Manufacturing width	standard		3000	mm	118.11	in.
	maximum		3000	mm	118.11	in.

Fabrication

Hot splicing is always preferable. Glueing can only be done when the belt is exposed to normal temperature and the humidity is not excessive. For the working method, consult the splice information and the equipment literature. Apply the recommended splice as indicated in the seperate information.

Additional information

This sheet contains typical values, which apply to a temperature of approx. 20 °C (68 °F), unless otherwise stated, individual data may differ.

We recommend to keep the belt tension to a practical working minimum to maximize the service life of the belt and machine parts.

Always protect belts from sunlight/UV-radiation, avoid temperatures below 10°C and above 40°C, dust and dirt. Store belts in a cool and dry place and if possible in their original packaging.

For details consult 'Storage and handling instructions' or contact our specialist.