Technical datasheet

Ropanyl EM 6/2 00+02 dark green M1 AS FG



Article code: SBVL589909

General information							
Product group	Synthetic Belts						
Main product feature	Antistatic, Foodgrade						
Indication of use	Flat, Slider bed						
Belt construction							
Tension layer	polyester, stable						
Number of plies		2					
Top side	material	al Ropanyl, TPU					
	finish	finish smooth, M1 Fine matt finish					
	color	dark green					
Bottom side	material	material Ropanol, PUR					
	finish	impregnated fabric					
	color	natural	natural				
Characteristics							
Food Grade (FG)	yes	FDA					
Antistatic (AS)	yes	yes ISO 21178					
High conductive (HC)	no						
Flame-retardant (FR)	no						
ATEX approval	no						
Technical data							
Hardness	ISO 868	top side	92A	Shore			
Force at 1% elongation (static)	ISO 21181			N/mm		lbs/in.	
Thickness	AB method KV.002	total	1.5	mm	0.06	in.	
Weight	AB method KV.004			kg/m²		lbs/ft²	
Operating temperature	continuous	from / to	-20 / 90	°C	-4 / 194	°F	
	short	from / to	-30 / 110	°C	-22 / 230	°F	
Minimum pulley diameter	flexing		15	mm	0.59	in.	
	backflexing		25	mm	0.98	in.	
Manufacturing width	standard		1829	mm	72.01	in.	
	maximum		1829	mm	72.01	in.	

Fabrication

Hot splicing is always preferable. Glueing can only be done when the belt is exposed to normal temperature and the humidity is not excessive. For the working method, consult the splice information and the equipment literature. Apply the recommended splice as indicated in the seperate information.

Additional information

This sheet contains typical values, which apply to a temperature of approx. 20 °C (68 °F), unless otherwise stated, individual data may differ. We recommend to keep the belt tension to a practical working minimum to maximize the service life of the belt and machine parts.

Always protect belts from sunlight/UV-radiation, avoid temperatures below 10°C and above 40°C, dust and dirt. Store belts in a cool and dry place and if possible in their original packaging.

For details consult 'Storage and handling instructions' or contact our specialist.

Because of continuous development, the presented data is subject to alteration. This data replaces that included in previous publications. Ammeraal Beltech excludes any liability for the incorrect use of the above stated information. Subject to the general terms and conditions of sale and delivery, as applied by its operating companies, are all activities performed and services rendered by Ammeraal Beltech.