**Technical datasheet** 

# SBR EF 16/2 00+C52 tan CR HR

### Article code: LWSB560455



General information			
Product group Light Weight Rubber			
Industry segment	General industry		
Main product feature Cold resistant, Heat resistant			
Application In/declined conveying			
Indication of use	In/declined conveying, Slider bed, Rollers, Flat		
Belt construction			
Tension laver	REL polyester multifilament flexible		

ве	τ	CO	ns	στru	ιςτ	ion	

Tension layer	RFL polyester multifilament, flexible
Number of plies	2
Top side mater	ial SBR, SBR
finish	profile, C52 Diamond impression profile
color	tan
Bottom side mater	fabric, polyester
finish	impregnated
color	red
Chauseteristics	

## Characteristics

Food Grade (FG)
Flame-retardant (FR)

Technical data						
Hardness	ISO 868	top side	40A	Shore		
Force at 1% elongation	ISO 21181		16	N/mm	91.36	lbs/in.
Thickness	AB method KV.002	belt	7.9	mm	0.31	in.
		top cover	6.9	mm	0.27	in.
Weight	AB method KV.004		6.2	kg/m²	1.27	lbs/ft²
Operating temperature	continuous	from / to	-40 / 121	°C	-40 / 249.8	°F
	short	from / to	-40 / 121	°C	-40 / 249.8	°F
Minimum pulley diameter	flexing		127	mm	5	in.
	backflexing		63.5	mm	2.5	in.
Manufacturing width	standard		1829	mm	72.01	in.
	maximum		1829	mm	72.01	in.

#### Fabrication

Vulcanizing is always preferable. Cold splicing can only be done when the belt is exposed to normal temperature and the humidity is not excessive. For the working method, consult the splice information and the equipment literature. Apply the recommended splice as indicated in the seperate information.

#### **Additional information**

This sheet contains typical values, which apply to a temperature of approx. 20 °C (68 °F), unless otherwise stated, individual data may differ. We recommend to keep the belt tension to a practical working minimum to maximize the service life of the belt and machine parts.

Always protect belts from sunlight/UV-radiation, avoid temperatures below 10°C and above 40°C, dust and dirt. Store belts in a cool and dry place and if possible in their original packaging.

For details consult 'Storage and handling instructions' or contact our specialist.

no no

Because of continuous development, the presented data is subject to alteration. This data replaces that included in previous publications. Ammeraal Beltech excludes any liability for the incorrect use of the above stated information. Subject to the general terms and conditions of sale and delivery, as applied by its operating companies, are all activities performed and services rendered by Ammeraal Beltech.