Technical datasheet

Ropanol ESF 7/2 00+00 (PU) white FG

Ammeraal Beltech
Innovation & Service in Belting

Article code: SBCP0349U2

General information	
Product group	Synthetic Belts
Industry segment	Food
Main product feature	Foodgrade
Indication of use	Flat, Rollers, Troughed, Slider bed

Belt construction		
Tension layer		polyester spun, flexible
Number of plies		2
Top side	material	Ropanol, PUR
	finish	impregnated fabric
	color	white
Bottom side	material	Ropanol, PUR
	finish	impregnated fabric
	color	transparent

Characteristics		
Food Grade (FG)	yes	EC 1935/2004, EU 10/2011; FDA
Antistatic (AS)	no	
High conductive (HC)	no	
Flame-retardant (FR)	no	
ATEX approval	no	

Technical data						
Force at 1% elongation (static)	ISO 21181		7	N/mm	39.97	lbs/in.
Thickness	AB method KV.002	total	2.00	mm	0.08	in.
Weight	AB method KV.004		1.7	kg/m²	0.35	lbs/ft²
Operating temperature	continuous	from / to	-20 / 90	°C	-4 / 194	°F
	short	from / to	-30 / 110	°C	-22 / 230	°F
Minimum pulley diameter	flexing		20	mm	0.79	in.
	backflexing		25	mm	0.98	in.
Manufacturing width	standard		1900	mm	74.8	in.
	maximum		1900	mm	74.8	in.

Fabrication

Hot splicing is always preferable. Glueing can only be done when the belt is exposed to normal temperature and the humidity is not excessive. For the working method, consult the splice information and the equipment literature. Apply the recommended splice as indicated in the seperate information.

Additional information

This sheet contains typical values, which apply to a temperature of approx. 20 °C (68 °F), unless otherwise stated, individual data may differ. We recommend to keep the belt tension to a practical working minimum to maximize the service life of the belt and machine parts.

Always protect belts from sunlight/UV-radiation, avoid temperatures below 10°C and above 40°C, dust and dirt. Store belts in a cool and dry place and if possible in their original packaging.

For details consult 'Storage and handling instructions' or contact our specialist.

Because of continuous development, the presented data above stated information. Subject to the general terms			aal Beltech excludes any liability for the incorrect s performed and services rendered by Ammeraa	
© Ammeraal Beltech SB001 English A4	Modified: Monday, August 28, 2023,	Printed: Thursday, October 26, 2023		Page:2 /