Technical datasheet

PVCEXCON 4F/30 W74 V08/V20 AS AR FA FR ATEX



Article code: SBMD000072

General information		
Product group	Synthetic Belts	
Belt construction		
Number of plies		4
Top side	material	PVCEXCON, PVCEXCON
Bottom side	material	PVCEXCON

Fabrication

Hot splicing is always preferable. Glueing can only be done when the belt is exposed to normal temperature and the humidity is not excessive. For the working method, consult the splice information and the equipment literature. Apply the recommended splice as indicated in the seperate information.

Additional information

This sheet contains typical values, which apply to a temperature of approx. 20 $^{\circ}$ C (68 $^{\circ}$ F), unless otherwise stated, individual data may differ.

We recommend to keep the belt tension to a practical working minimum to maximize the service life of the belt and machine parts.

Always protect belts from sunlight/UV-radiation, avoid temperatures below 10°C and above 40°C, dust and dirt. Store belts in a cool and dry place and if possible in their original packaging.

For details consult 'Storage and handling instructions' or contact our specialist.