

# Flexam E郑 10/1 0+A42 black /5.1 mm

Article code: SBFL589375

## General information

<b>Product group</b>	Synthetic Belts
<b>Indication of use</b>	Flat, Radius conveying, Rollers

## Belt construction

<b>Tension layer</b>		polyester spiral, stable
<b>Number of plies</b>		1
<b>Top side</b>	<b>material</b>	Flexam, PVC
	<b>finish</b>	profile, A42 Supergrip wave profile
	<b>color</b>	black
<b>Bottom side</b>	<b>material</b>	fabric, polyester spiral
	<b>finish</b>	bare fabric
	<b>color</b>	white

## Characteristics

<b>Food Grade (FG)</b>	no
<b>Antistatic (AS)</b>	no
<b>High conductive (HC)</b>	no
<b>ATEX approval</b>	no

## Technical data

<b>Hardness</b>	ISO 868	top side	55A Shore	
<b>Force at 1% elongation (static)</b>	ISO 21181		10 N/mm	57.1 lbs/in.
<b>Thickness</b>	AB method KV.002	total	5.10 mm	0.2 in.
		top cover	2.70 mm	0.11 in.
<b>Operating temperature</b>	continuous	from / to	-15 / 80 °C	5 / 176 °F
	short	from / to	-15 / 100 °C	5 / 212 °F
<b>Minimum pulley diameter</b>	flexing		40 mm	1.57 in.
	backflexing		80 mm	3.15 in.
<b>Manufacturing width</b>	standard		2000 mm	78.74 in.
	maximum		2000 mm	78.74 in.

## Fabrication

Hot splicing is always preferable. Glueing can only be done when the belt is exposed to normal temperature and the humidity is not excessive. For the working method, consult the splice information and the equipment literature. Apply the recommended splice as indicated in the separate information.

## Additional information

This sheet contains typical values, which apply to a temperature of approx. 20 °C (68 °F), unless otherwise stated, individual data may differ. We recommend to keep the belt tension to a practical working minimum to maximize the service life of the belt and machine parts. Always protect belts from sunlight/UV-radiation, avoid temperatures below 10°C and above 40°C, dust and dirt. Store belts in a cool and dry place and if possible in their original packaging. For details consult 'Storage and handling instructions' or contact our specialist.