

## Nitrile BX EP 12/3 C5+C5 white CR AS FR FG

Article code: LWNX560212



## General information

<b>Product group</b>	Light Weight Rubber
<b>Main product feature</b>	Cold resistant, Antistatic, Flame retardant, Foodgrade

## Belt construction

<b>Tension layer</b>		RFL polyester/nylon, flexible
<b>Number of plies</b>		3
<b>Top side</b>	<b>material</b>	Nitrile BX, NX
	<b>finish</b>	profile, C5 Light fabric profile
	<b>color</b>	white
<b>Bottom side</b>	<b>material</b>	Nitrile BX, NX
	<b>finish</b>	profile
	<b>color</b>	white

## Characteristics

<b>Food Grade (FG)</b>	yes	FDA
<b>Antistatic (AS)</b>	yes	
<b>Flame-retardant (FR)</b>	yes	
<b>ATEX approval</b>	ATEX 2	

## Technical data

<b>Hardness</b>	ISO 868	top side	70A Shore	
<b>Force at 1% elongation</b>	ISO 21181		12 N/mm	68.52 lbs/in.
<b>Thickness</b>	AB method KV.002	belt	6.7 mm	0.26 in.
		top cover	1.2 mm	0.05 in.
<b>Weight</b>	AB method KV.004		8.5 kg/m <sup>2</sup>	1.74 lbs/ft <sup>2</sup>
<b>Operating temperature</b>	continuous	from / to	-18 / 121 °C	-0.4 / 249.8 °F
	short	from / to	-18 / 121 °C	-0.4 / 249.8 °F
<b>Manufacturing width</b>	standard		1524 mm	60 in.
	maximum		1524 mm	60 in.

## Fabrication

Vulcanizing is always preferable. Cold splicing can only be done when the belt is exposed to normal temperature and the humidity is not excessive. For the working method, consult the splice information and the equipment literature. Apply the recommended splice as indicated in the separate information.

## Additional information

This sheet contains typical values, which apply to a temperature of approx. 20 °C (68 °F), unless otherwise stated, individual data may differ.

We recommend to keep the belt tension to a practical working minimum to maximize the service life of the belt and machine parts.

Always protect belts from sunlight/UV-radiation, avoid temperatures below 10°C and above 40°C, dust and dirt. Store belts in a cool and dry place and if possible in their original packaging.

For details consult 'Storage and handling instructions' or contact our specialist.

Because of continuous development, the presented data is subject to alteration. This data replaces that included in previous publications. Ammeraal Beltech excludes any liability for the incorrect use of the above stated information. Subject to the general terms and conditions of sale and delivery, as applied by its operating companies, are all activities performed and services rendered by Ammeraal Beltech.