Endless Woven GK8486BP AmDough Cotton 2.8mm



Article code: RMFA000085

Article code. Kirii A000005							
General information							
Product group	endless woven	endless woven					
Industry segment	Food: Bakery	Food: Bakery					
Main product feature	Foodgrade, Mois	Foodgrade, Moisture absorbant, Non-fraying					
Application	Rotary moulder	Rotary moulder belt, Rotary cutter, Oven infeed belt					
Indication of use	Knife edge trans	Knife edge transfer, Abrasive applications					
Belt construction							
Tension layer		broken	twill, cotton-polyamide				
Number of plies		1					
Bottom side	material	material Ropanol, PUR					
	finish	finish impregnation					
		transparent					
Characteristics							
Food Grade (FG)	yes	EC 1935	/2004, EU 10-2011; FDA				
To the last date							
Technical data	ISO 21181			120	NI /	605.22	Us a Cos
Tensile Strength Thickness	150 21181		total	2.8	N/mm	685.22 0.11	•
Weight			totai		kg/m ²		lbs/ft²
Length			min. / max.	800 / 52000	-	31.5 / 2047.24	•
Width			min. / max.	40 / 3400		1.57 / 133.86	
Operating temperature	continuous		from / to	-10 / 90	°C	14 / 194	°F
	short		from / to	-30 / 110	°C	-22 / 230	°F
Minimum pulley diameter				5	mm	0.2	in.
Tolerances							
Length	± 2 %		minimum ±	20	mm	0.79	in.
Width	± 2 %		minimum ±	2	mm	0.08	in.
Thickness			±	0.5	mm	0.02	in.

Process and Conveyor	Belt

Top view



Belttype	Material	Weave	Belt Thickness [mm]
AmDough 100	cotton	broken twill	2.8
AmDough 90	cotton	broken twill	2.4
AmDough 80	cotton / polyamide	broken twill	2.4
AmDough 70	cotton	plain	2.0
AmDough 60	cotton / polyamide	broken twill	2.4
AmDough 50	cotton / polyamide	plain	1.8
AmDough 40	cotton / polyamide	plain	2.0
AmDough 20	cotton / polyester	plain	2.0

There is a linear relationship between the AmDough absorption numbers:

Heavy dough: wet, high degree of moisture, AmDough belt with higher absorption factor

Light dough: dry, low degree of moisture, AmDough belt with lower absorption factor

Top side: always uncoated

Bottom side: PUR transparent food grade impregnation for stability, better wear resistance and longer belt life

Belt edges are reinforced with polyamide selvedges.

Dimension: length up to 100 m, width up to 3400 mm

Broken twill (GK) types are also available as Twill (k) versions.

Additional information

This sheet contains typical values, which apply to a temperature of approx. 20 °C (68 °F), unless otherwise stated, individual data may differ.

Diameter of knife edge <135° [mm]
5
4
4
3
4
3
3
3