Technical datasheet

Solicord V-belt TPE 55D Beige SM FG 22x14



Article code: SCVB000030

General information							
Product group	SoliCord						
Construction							
Material	TPE						
(Top)surface finish	smooth						
Color	beige						
Shape	Vee						
Execution	solid						
Characteristics							
Food Grade (FG)	yes	all foodstuff	; all foodstuff				
Antistatic (AS)	no						
ATEX approval	no						
Fechnical data							
Hardness	ISO 868			55D	Shore		
Recommended pre-tension				3	%		
Working tension				50	daN/cm ²		
Diameter				0	mm	0	in.
Cross section				2.4	cm²		
Weight				0.29	kg/m	0.06	lb/ft
Operating temperature	continuous		from / to	-30 / 100	°C	-22 / 212	°F
Minimum pulley diameter				230	mm	9.06	in.
Coefficient of friction	against steel		dynamic	0,35			
	against PE			0,15			
	against HDPE			0,1			
Manufacturing length	maximum			50000	mm	1968.5	in.
Fabrication							
Recommended splice types	Butt weld						
Splice equipment	Only use equipment supplied or approved by Ammeraal Beltech.						
Splicing on site	Always first ma	ake a test splice	e to confirm the rig	ht settings and p	proper pre-heating	ng of the equipme	ent.

Additional information

This sheet contains typical values, which apply to a temperature of approx. 20 °C (68 °F), unless otherwise stated, individual data may differ. Keep the belt tension to a practical working minimum for maximum belt and machine life.

Always protect belts from sunlight/UV-radiation, avoid temperatures below 10°C and above 40°C, dust and dirt.

Because of continuous development, the presented data is subject to alteration. This data replaces that included in previous publications. Ammeraal Beltech excludes any liability for the incorrect use of the above stated information. Subject to the general terms and conditions of sale and delivery, as applied by its operating companies, are all activities performed and services rendered by Ammeraal Beltech.