

Nitrile BX EP 8/2 C5+C5 white CR AS FR FG

Article code: LWCN560229

General information

Product group	Light Weight Rubber
Industry segment	Food
Main product feature	Cold resistant, Antistatic, Flame retardant, Foodgrade
Indication of use	Flat, Troughed, Rollers, Slider bed

Belt construction

Tension layer		RFL polyester/nylon, flexible
Number of plies		2
Top side	material	Nitrile BX, Nitrile
	finish	profile, C5 Light fabric profile
	color	white
Bottom side	material	Nitrile, Nitrile
	finish	profile
	color	white

Characteristics

Food Grade (FG)	yes	FDA
Antistatic (AS)	yes	
Flame-retardant (FR)	yes	

Technical data

Hardness	ISO 868	top side	70A Shore	
Force at 1% elongation	ISO 21181		12 N/mm	68.52 lbs/in.
Thickness	AB method KV.002	belt	4.3 mm	0.17 in.
		top cover	1.2 mm	0.05 in.
Weight	AB method KV.004		6.2 kg/m ²	1.27 lbs/ft ²
Operating temperature	continuous	from / to	-18 / 121 °C	-0.4 / 249.8 °F
	short	from / to	-18 / 121 °C	-0.4 / 249.8 °F
Minimum pulley diameter	flexing		101.6 mm	4 in.
	backflexing		101.6 mm	4 in.
Manufacturing width	standard		1829 mm	72.01 in.
	maximum		1829 mm	72.01 in.

Fabrication

Vulcanizing is always preferable. Cold splicing can only be done when the belt is exposed to normal temperature and the humidity is not excessive. For the working method, consult the splice information and the equipment literature. Apply the recommended splice as indicated in the separate information.

Additional information

This sheet contains typical values, which apply to a temperature of approx. 20 °C (68 °F), unless otherwise stated, individual data may differ.

We recommend to keep the belt tension to a practical working minimum to maximize the service life of the belt and machine parts.

Always protect belts from sunlight/UV-radiation, avoid temperatures below 10°C and above 40°C, dust and dirt. Store belts in a cool and dry place and if possible in their original packaging.

For details consult 'Storage and handling instructions' or contact our specialist.

Because of continuous development, the presented data is subject to alteration. This data replaces that included in previous publications. Ammeraal Beltech excludes any liability for the incorrect use of the above stated information. Subject to the general terms and conditions of sale and delivery, as applied by its operating companies, are all activities performed and services rendered by Ammeraal Beltech.