

Solicord Round belt TPU 85A Sapphire Blue SM FG 40

Article code: SCRB000057

General information

| | |
|---------------|----------|
| Product group | SoliCord |
|---------------|----------|

Construction

| | |
|---------------------|---------------|
| Material | TPU |
| (Top)surface finish | smooth |
| Color | Sapphire blue |
| Shape | Round |
| Execution | solid |

Characteristics

| | | |
|-----------------|-----|------------------------------|
| Food Grade (FG) | yes | all foodstuff; all foodstuff |
| Antistatic (AS) | no | |
| ATEX approval | no | |

Technical data

| | | | | |
|-------------------------|---------------|-----------|------------------------|--------------|
| Hardness | ISO 868 | | 88A Shore | |
| Recommended pre-tension | | | 7 % | |
| Working tension | | | 18 daN/cm ² | |
| Diameter | | | 4 mm | 0.16 in. |
| Cross section | | | 0.126 cm ² | |
| Weight | | | 0.016 kg/m | 0 lb/ft |
| Operating temperature | continuous | from / to | -30 / 80 °C | -22 / 176 °F |
| Minimum pulley diameter | | | 30 mm | 1.18 in. |
| Coefficient of friction | against steel | dynamic | 0,6 | |
| | against PE | | 0,3 | |
| | against HDPE | | 0,25 | |
| Manufacturing length | maximum | | 200000 mm | 7874.02 in. |

Fabrication

| | |
|--------------------------|--|
| Recommended splice types | Butt weld |
| Splice equipment | Only use equipment supplied or approved by Ammeraal Beltech. |
| Splicing on site | Always first make a test splice to confirm the right settings and proper pre-heating of the equipment. |

Additional information

This sheet contains typical values, which apply to a temperature of approx. 20 °C (68 °F), unless otherwise stated, individual data may differ.

Keep the belt tension to a practical working minimum for maximum belt and machine life.

Always protect belts from sunlight/UV-radiation, avoid temperatures below 10°C and above 40°C, dust and dirt.