Endless Woven P84XSBP AmDough50XS Cotton 1.8mm



0.5 mm

Article code: RMFA000055

Alticle code. KMFA000055							
General information							
Product group	endless woven	endless woven					
Industry segment	Food: Bakery	Food: Bakery					
Main product feature	Foodgrade, Mois	Foodgrade, Moisture absorbant, Non-fraying					
Application	Rotary moulder l	Rotary moulder belt, Rotary cutter, Oven infeed belt					
Indication of use	Knife edge trans	Knife edge transfer, Abrasive applications					
Belt construction							
Tension layer		Plain, co	otton-polyamide				
Number of plies		1					
Bottom side	material	Ropanol	Ropanol, PUR				
	finish	impregnation					
		transpar	rent				
Characteristics							
Food Grade (FG)	yes	EC 1935	/2004, EU 10-2011; FDA				
Technical data							
Tensile Strength	ISO 21181			100 N/mm	571.01 lbs/in.		
Thickness			total	1.8 mm	0.07 in.		
Weight				1.3 kg/m ²	0.27 lbs/ft²		
Length			min. / max.	800 / 52000 mm	31.5 / 2047.24 in.		
Width			min. / max.	40 / 3400 mm	1.57 / 133.86 in.		
Operating temperature	continuous		from / to	-10 / 90 °C	14 / 194 °F		
Minimum mullan diameter	short		from / to	-30 / 110 °C	-22 / 230 °F		
Minimum pulley diameter				3 mm	0.12 in.		
Tolerances							
Length	± 2 %		minimum ±	20 mm	0.79 in.		
Width	± 2 %		minimum ±	2 mm	0.08 in.		

Thickness

0.02 in.

Process and Conveyor	Belt

Top view



Belttype	Material	Weave	Belt Thickness [mm]
AmDough 100	cotton	broken twill	2.8
AmDough 90	cotton	broken twill	2.4
AmDough 80	cotton / polyamide	broken twill	2.4
AmDough 70	cotton	plain	2.0
AmDough 60	cotton / polyamide	broken twill	2.4
AmDough 50	cotton / polyamide	plain	1.8
AmDough 40	cotton / polyamide	plain	2.0
AmDough 20	cotton / polyester	plain	2.0

There is a linear relationship between the AmDough absorption numbers:

Heavy dough: wet, high degree of moisture, AmDough belt with higher absorption factor

Light dough: dry, low degree of moisture, AmDough belt with lower absorption factor

Top side: always uncoated

Bottom side: PUR transparent food grade impregnation for stability, better wear resistance and longer belt life

Belt edges are reinforced with polyamide selvedges.

Dimension: length up to 100 m, width up to 3400 mm

Broken twill (GK) types are also available as Twill (k) versions.

Additional information

This sheet contains typical values, which apply to a temperature of approx. 20 °C (68 °F), unless otherwise stated, individual data may differ.

Diameter of knife edge <135° [mm]
5
4
4
3
4
3
3
3