

Flexam MPLY/M 12/2 0+00 dark grey

Article code: SBFL514228

General information

Product group	Synthetic Belts
Industry segment	Building materials; Metal; Automotive
Main product feature	Impact resistant
Indication of use	Slider bed, Rollers, Flat

Belt construction

Tension layer		polyester, stable
Number of plies		2
Top side	material	Flexam, PVC
	finish	impregnated fabric
	color	dark grey
Bottom side	material	fabric, polyester
	finish	bare fabric
	color	natural

Characteristics

Food Grade (FG)	no	
Antistatic (AS)	no	
High conductive (HC)	no	
ATEX approval	no	

Technical data

Force at 1% elongation (static)	ISO 21181		12 N/mm	68.52 lbs/in.
Thickness	AB method KV.002	total	3.40 mm	0.13 in.
		top cover	0.00 mm	0 in.
Weight	AB method KV.004		3.5 kg/m ²	0.72 lbs/ft ²
Operating temperature	continuous	from / to	-15 / 80 °C	5 / 176 °F
	short	from / to	-15 / 100 °C	5 / 212 °F
Minimum pulley diameter	flexing		80 mm	3.15 in.
	backflexing		100 mm	3.94 in.
Manufacturing width	standard		2000 mm	78.74 in.
	maximum		2000 mm	78.74 in.

Fabrication

Hot splicing is always preferable. Glueing can only be done when the belt is exposed to normal temperature and the humidity is not excessive.

For the working method, consult the splice information and the equipment literature. Apply the recommended splice as indicated in the separate information.

Additional information

This sheet contains typical values, which apply to a temperature of approx. 20 °C (68 °F), unless otherwise stated, individual data may differ.

We recommend to keep the belt tension to a practical working minimum to maximize the service life of the belt and machine parts.

Always protect belts from sunlight/UV-radiation, avoid temperatures below 10°C and above 40°C, dust and dirt. Store belts in a cool and dry place and if possible in their original packaging.

For details consult 'Storage and handling instructions' or contact our specialist.