**Technical datasheet** 

## PVC 125 00+01 black FR IR

Article code: SBAS589533



General information	
Product group	Synthetic Belts
Main product feature	Non logo, Impact resistant
Indication of use	Slider bed, Rollers, Flat

Belt construction		
Tension layer		polyester, flexible
Number of plies		1
Top side	material	PVC, PVC
	finish	impregnated fabric
	color	black
Bottom side	material	PVC, PVC
	finish	impregnated fabric

Characteristics		
Food Grade (FG)	no	
Antistatic (AS)	no	
High conductive (HC)	no	
Flame-retardant	no	
	no	
ATEX approval	no	

Technical data						
Force at 1% elongation (static)	ISO 21181		21	N/mm	119.91	lbs/in.
Thickness	AB method KV.002	total	3.80	mm	0.15	in.
		top cover	00	mm	0	in.
Weight	AB method KV.004		3.6	kg/m²	0.74	lbs/ft²
Operating temperature	continuous	from / to	-15 / 80	°C	5 / 176	°F
	short	from / to	-15 / 100	°C	5 / 212	°F
Minimum pulley diameter	flexing		70	mm	2.76	in.
	backflexing		70	mm	2.76	in.
Manufacturing width	standard		2400	mm	94.49	in.
	maximum		2400	mm	94.49	in.

## **Fabrication**

Hot splicing is always preferable. Glueing can only be done when the belt is exposed to normal temperature and the humidity is not excessive. For the working method, consult the splice information and the equipment literature. Apply the recommended splice as indicated in the seperate information.

## **Additional information**

This sheet contains typical values, which apply to a temperature of approx. 20 °C (68 °F), unless otherwise stated, individual data may differ. We recommend to keep the belt tension to a practical working minimum to maximize the service life of the belt and machine parts.

Always protect belts from sunlight/UV-radiation, avoid temperatures below 10°C and above 40°C, dust and dirt. Store belts in a cool and dry place and if possible in their original packaging.

For details consult 'Storage and handling instructions' or contact our specialist.