

PVCCON | 1LR/5 DBS17 00/V09 AB AS

Article code: SBMD000237



General information

Product group Synthetic Belts

Belt construction

Tension layer		polyester, 0
Number of plies		0
Top side	material	PVCCON, 0
	finish	None, 0
	color	0
Bottom side	material	PVCCON, 0
	finish	0
	color	0

Characteristics

Food Grade (FG)	no
Antistatic (AS)	no
Flame-retardant (FR)	no
ATEX approval	no

Technical data

Hardness	ISO 868	top side	0 Shore	
Force at 1% elongation (static)	ISO 21181		0 N/mm	0 lbs/in.
Thickness	AB method KV.002	total	0.00 mm	0 in.
		top cover	0 mm	0 in.
Weight	AB method KV.004		0 kg/m ²	0 lbs/ft ²
Operating temperature	continuous	from / to	-18 / -18 °C	-0.4 / -0.4 °F
Minimum pulley diameter	flexing		0 mm	0 in.
	backflexing		0 mm	0 in.
Manufacturing width	standard		0 mm	0 in.
	maximum		0 mm	0 in.

Fabrication

Hot splicing is always preferable. Glueing can only be done when the belt is exposed to normal temperature and the humidity is not excessive. For the working method, consult the splice information and the equipment literature. Apply the recommended splice as indicated in the separate information.

Additional information

This sheet contains typical values, which apply to a temperature of approx. 20 °C (68 °F), unless otherwise stated, individual data may differ. We recommend to keep the belt tension to a practical working minimum to maximize the service life of the belt and machine parts. Always protect belts from sunlight/UV-radiation, avoid temperatures below 10°C and above 40°C, dust and dirt. Store belts in a cool and dry place and if possible in their original packaging. For details consult 'Storage and handling instructions' or contact our specialist.