Technical datasheet

Ropanyl EF 10/2 00+02 white FG

Article code: SBRY592921



General information	
Product group	Synthetic Belts
Industry segment	Food: Confectionary & candy, Bakery; Container & packaging
Main product feature	Foodgrade
Indication of use	Slider bed, Rollers, Flat

Belt construction		
Tension layer		polyester, flexible
Number of plies		2
Top side	material	Ropanyl, TPU
	finish	smooth, glossy
	color	white
Bottom side	material	Ropanol, PUR
	finish	impregnated fabric
	color	white

Characteristics		
Food Grade (FG)	yes	FDA
Antistatic (AS)	no	
High conductive (HC)	no	
Flame-retardant (FR)	no	
ATEX approval	no	

Technical data								
Hardness	ISO 868	top side	93A	Shore				
Force at 1% elongation (static)	ISO 21181		10	N/mm	57.1	lbs/in.		
Thickness	AB method KV.002	total	1.2	mm	0.05	in.		
		top cover	0.2	mm	0.01	in.		
Weight	AB method KV.004		1.3	kg/m²	0.27	lbs/ft²		
Operating temperature	continuous	from / to	-20 / 90	°C	-4 / 194	°F		
	short	from / to	-30 / 110	°C	-22 / 230	°F		
Minimum pulley diameter	flexing		8	mm	0.31	in.		
	backflexing		20	mm	0.79	in.		
Manufacturing width	standard		2000	mm	78.74	in.		
	maximum		2000	mm	78.74	in.		

Fabrication

Hot splicing is always preferable. Glueing can only be done when the belt is exposed to normal temperature and the humidity is not excessive. For the working method, consult the splice information and the equipment literature. Apply the recommended splice as indicated in the seperate information.

Additional information

This sheet contains typical values, which apply to a temperature of approx. 20 °C (68 °F), unless otherwise stated, individual data may differ.

We recommend to keep the belt tension to a practical working minimum to maximize the service life of the belt and machine parts.

Always protect belts from sunlight/UV-radiation, avoid temperatures below 10°C and above 40°C, dust and dirt. Store belts in a cool and dry place and if possible in their original packaging.

For details consult 'Storage and handling instructions' or contact our specialist.

Because of continuous development, the presented data is subject to alteration. This data replaces that included in previous publications. Ammeraal Beltech excludes any liability for the incorrect use of the above stated information. Subject to the general terms and conditions of sale and delivery, as applied by its operating companies, are all activities performed and services rendered by Ammeraal Beltech.