Technical datasheet

Flexam EM 10/2 00+P41 light blue FG

Article code: SBFL514985



General information				
Product group	Synthetic Belts			
Industry segment	Food			
Main product feature	Foodgrade, Oil & grease resistant			
Indication of use	Slider bed, Rollers, Flat			

Belt construction		
Tension layer		polyester, stable
Number of plies		2
Top side	material	Flexam, PVC
	finish	profile, P41 Transversal ribs profile
	color	Light blue
Bottom side	material	Flexam, PVC
	finish	impregnated fabric
	color	transparent

Characteristics		
Food Grade (FG)	yes	EC 1935/2004, EU 10/2011; FDA
Antistatic (AS)	no	
High conductive (HC)	no	
ATEX approval	no	

Technical data								
Hardness	ISO 868	top side	80A	Shore				
Force at 1% elongation (static)	ISO 21181		10	N/mm	57.1	lbs/in.		
Thickness	AB method KV.002	total	5.70	mm	0.22	in.		
		top cover	4.10	mm	0.16	in.		
Weight	AB method KV.004		3.9	kg/m²	0.8	lbs/ft²		
Operating temperature	continuous	from / to	-15 / 80	°C	5 / 176	°F		
	short	from / to	-15 / 100	°C	5 / 212	°F		
Minimum pulley diameter	flexing		50	mm	1.97	in.		
	backflexing		90	mm	3.54	in.		
Manufacturing width	standard		1500	mm	59.06	in.		
	maximum		1500	mm	59.06	in.		

Fabrication

Hot splicing is always preferable. Glueing can only be done when the belt is exposed to normal temperature and the humidity is not excessive. For the working method, consult the splice information and the equipment literature. Apply the recommended splice as indicated in the seperate information.

Additional information

This sheet contains typical values, which apply to a temperature of approx. 20 °C (68 °F), unless otherwise stated, individual data may differ.

We recommend to keep the belt tension to a practical working minimum to maximize the service life of the belt and machine parts.

Always protect belts from sunlight/UV-radiation, avoid temperatures below 10°C and above 40°C, dust and dirt. Store belts in a cool and dry place and if possible in their original packaging.

For details consult 'Storage and handling instructions' or contact our specialist.