**Technical datasheet** 

**General information** 

## NR EZP 10/1 01+32 red

Article code: ZLNR583070



Product group	Ziplink	
Belt construction		
Tension layer		Ziplink fabric, flexible
Number of plies		1
Top side	material	NR, NR
	finish	smooth
	color	red
Bottom side	material	SBR, polyester
	finish	friction
	color	black

Technical data						
Hardness	ISO 868	top side	40A	Shore		
Force at 1% elongation	ISO 21181		10	N/mm	57.1	lbs/in.
Thickness	AB method KV.002		5.1	mm	0.2	in.
Weight	AB method KV.004		5.8	kg/m²	1.19	lbs/ft²
Operating temperature	continuous	from / to	-40 / 121	°C	-40 / 249.8	°F
	short	from / to	-40 / 121	°C	-40 / 249.8	°F
Manufacturing width	standard		1829	mm	72.01	in.
	maximum		1829	mm	72.01	in.

## **Fabrication**

Ziplink belts can be endlessed, very easy and quick splicing without presses, fasteners or glues. Refer to the technical information for more information about splicing of Ziplink belts.

## **Additional information**

This sheet contains typical values, which apply to a temperature of approx. 20 °C (68 °F), unless otherwise stated, individual data may differ.

We recommend to keep the belt tension to a practical working minimum to maximize the service life of the belt and machine parts.

Always protect belts from sunlight/UV-radiation, avoid temperatures below 10°C and above 40°C, dust and dirt. Store belts in a cool and dry place and if possible in their original packaging.

For details consult 'Storage and handling instructions' or contact our specialist.

Because of continuous development, the presented data is subject to alteration. This data above stated information. Subject to the general terms and conditions of sale and delivery	replaces that included in previous publication y, as applied by its operating companies, are	ns. Ammeraal Beltech excludes any liability all activities performed and services render	for the incorrect use of the ed by Ammeraal Beltech.