
Technical datasheet

## Nonex EE/1 00+A54 light blue FG AM

Article code: SBN0585033



۵dd	itiona	al info	rmation
Auu			mation

Minimum pulley diameter

Manufacturing width

Weight

Fabrication

information.

This sheet contains typical values, which apply to a temperature of approx. 20 °C (68 °F), unless otherwise stated, individual data may differ. We recommend to keep the belt tension to a practical working minimum to maximize the service life of the belt and machine parts.

Hot splicing is always preferable. Glueing can only be done when the belt is exposed to normal temperature and the humidity is not excessive. For the working method, consult the splice information and the equipment literature. Apply the recommended splice as indicated in the seperate

Always protect belts from sunlight/UV-radiation, avoid temperatures below 10°C and above 40°C, dust and dirt. Store belts in a cool and dry place and if possible in their original packaging.

For details consult 'Storage and handling instructions' or contact our specialist.

AB method KV.004

flexing

backflexing

standard

maximum

Ammeraal Beltech

1.6 kg/m<sup>2</sup>

60 mm

80 mm

2000 mm

2000 mm

Innovation & Service in

0.33 lbs/ft<sup>2</sup>

2.36 in.

3.15 in.

78.74 in.

78.74 in.

Because of continuous development, the presented data is subject to alteration. This data replaces that included in previous publications. Ammeraal Beltech excludes any liability for the incorrect use of the above stated information. Subject to the general terms and conditions of sale and delivery, as applied by its operating companies, are all activities performed and services rendered by Ammeraal Beltech.