Technical datasheet

# PU linear HK 300 Steel K13




Article code: TBPU000250


General information							
Productgroup	Timing belts, PU Lin	iear					
Industry segment	Building materials;	Appliances; C	Container & packaging				
Main product feature	Positive drive, Wear	resistant					
Belt construction							
Tension member		steel					
Material	body	Polyurethan	e				
Surface	tooth side	Polyurethan	e				
	back side	Polyurethan	e				
Characteristics							
	20						
Food Grade (FG)	no						
Antistatic (AS)	no						
Oil & Fat resistance	yes						
To short of data							
Technical data	profile			Н			
Tooth	profile pitch			н 12.7	<b>m</b> m	0.5	in
Hardness body material	ISO 868				Shore	0.5	
Belt thickness	total				mm	0.17	in.
Belt weight					kg/m²		lbs/ft <sup>2</sup>
Coefficient of friction	tooth side to steel		dynamic	0,5			
Operating temperature	continuous		from / to	-10 / 80	°C	14 / 176	°F
Minimum pulley diameter	A) without counter f	flexing	number of teeth, t1	14			
			d1	55.23	mm	2.17	in.
			d2	60	mm	2.36	in.
	B) with counter flex	ing	number of teeth, t1	20			
			d1	79.48		3.13	
			d2		mm	3.15	
Endless length	minimum				mm	19.69	
Manufacturing length	standard			100000	mm	328.08	ft.

### **Reference images**

A) without counter flexing



## B) with counter flexing



### Fabrication

This information on the fabrication options is general, please contact Ammeraal Beltech for the specific fabrication possibilities of the timing belt of your choice.

Open end, prepared splice, spliced endless with mechanical fastener or a pin joint fastener.

Cleats welded or mechanically attached, metal teeth, guides welded or glued.

Covers can be welded, glued, coated or vulkanized onto the back side of the timing belt.

Thermoplastic covers can be embossed. Perforations, lateral and logitudinal slots, lateral and longitudinal profiles.

# **Additional Information**

Tooth profile according to standard: metric ISO 17396 , imperial ISO 5296-1, curvilinear ISO 13050, depending on the belt type. This sheet contains typical values, which apply to a temperature of approx. 20 °C (68 °F), unless otherwise stated, individual data may differ.

Consult our specialists for further information like technical calculations. Instructions regarding joining, storage & maintenance and tracking & tensioning.

Standard belt width [mm]	Allow. tensile load Linear open end & Torque [N]	Allow. tensile load Linear welded endless [N]	Spring force [N]
12.7	890	445	175000
19.1	1340	670	315000
25.4	1780	890	420000
38.1	2670	1335	630000
50.8	3560	1780	840000
76.2	5340	2670	1290000
101.61	7120	3560	1710000

Speed rpm [1/min]	Specific tooth force	Specific power [W/mm]
	[N/mm]	
0	4.53	0
25	4.352	0.023
50	4.235	0.045
75	4.104	0.065
100	4.011	0.085
150	3.845	0.122
200	3.722	0.158
300	3.507	0.223
400	3.341	0.283
500	3.205	0.339
750	2.952	0.469
1000	2.755	0.583
1250	2.603	0.689
1500	2.477	0.786
1750	2.369	0.878
2000	2.274	0.963
3000	1.984	1.26
4000	1.775	1.503

Standard

Because of continuous development, the presented data is subject to alteration. This data replaces that included in previous publications. Ammeraal Beltech excludes any liability for the incorrect use of the above stated information. Subject to the general terms and conditions of sale and delivery, as applied by its operating companies, are all activities performed and services rendered by Ammeraal Beltech.