# **PU linear HTD14M L Steel**

Article code: TBPU000251



General information	
Productgroup	Timing belts, PU Linear
Industry segment	General industry; Wood; Building materials: Stone & ceramics, Bricks & tiles
Main product feature	Positive drive, Wear resistant


Belt construction		
Tension member		steel
Material	body	Polyurethane
Surface	tooth side	Polyurethane
	back side	Polyurethane

Characteristics	
Food Grade (FG)	no
Antistatic (AS)	no
Oil & Fat resistance	yes


Technical data						
Tooth	profile		HTD14M			
	pitch		14	mm	0.55	in.
Hardness body material	ISO 868		92A	Shore		
Belt thickness	total		10	mm	0.39	in.
Belt weight			11.3	kg/m²	2.31	lbs/ft²
Coefficient of friction	tooth side to steel	dynamic	0,5			
Operating temperature	continuous	from / to	-10 / 80	°C	14 / 176	°F
Minimum pulley diameter	A) without counter flexing	number of teeth, t1	28			
		d1	122.13	mm	4.81	in.
		d2	120	mm	4.72	in.
	B) with counter flexing	number of teeth, t1	28			
		d1	122.13	mm	4.81	in.
		d2	180	mm	7.09	in.
Belt width	maximum		115	mm	4.53	in.
Endless length	minimum		1200	mm	47.24	in.
Manufacturing length	standard		100000	mm	328.08	ft.

#### Reference images


#### Side view



## A) without counter flexing



## B) with counter flexing



# Fabrication

This information on the fabrication options is general, please contact Ammeraal Beltech for the specific fabrication possibilities of the timing belt of your choice.

Open end, prepared splice, spliced endless with mechanical fastener or a pin joint fastener.

Cleats welded or mechanically attached, metal teeth, guides welded or glued.

Covers can be welded, glued, coated or vulkanized onto the back side of the timing belt.

Thermoplastic covers can be embossed. Perforations, lateral and logitudinal slots, lateral and longitudinal profiles.

#### **Additional Information**

Tooth profile according to standard: metric ISO 17396, imperial ISO 5296-1, curvilinear ISO 13050, depending on the belt type.

This sheet contains typical values, which apply to a temperature of approx. 20 °C (68 °F), unless otherwise stated, individual data may differ. Consult our specialists for further information like technical calculations. Instructions regarding joining, storage & maintenance and tracking & tensioning.

Standard belt width [mm]	Allow. tensile load Linear open end & Torque [N]	Allow. tensile load Linear welded endless [N]	Spring force [N]
25	5500	2750	1375000
40	9500	4750	2375000
55	13000	6500	3250000
70	17100	8550	4280000
85	21000	10500	5250000
100	24700	12350	6100000
115.1	28000	14000	7000000

Speed rpm [1/min] Specific tooth force [N/mm]
0 13
25 12.71 0.074
50 12.46 0.145
75 12.2 0.214
100 11.91 0.278
150 11.46 0.401
200 10.97 0.512
300 10.43 0.73
400 9.92 0.926
500 9.46 1.104
750 8.54 1.495
1000 7.81 1.822
7.22 2.106
1500 6.72 2.352
1750 6.28 2.564
2000 5.9 2.564
3000 4.71 2.753
4000 3.82 3.297

Standard

Because of continuous development, the presented data is subject to alteration. This data replaces that included in previous publications. Ammeraal Beltech excludes any liability for the incorrect use of the above stated information. Subject to the general terms and conditions of sale and delivery, as applied by its operating companies, are all activities performed and services rendered by Ammeraal Beltech.