Technical datasheet

## Ropanyl ESM 6/1 F1+A16 light blue FG AM NF



## Article code: SBRY595162

General information					
Product group	Synthetic Belts	Synthetic Belts			
Industry segment	Food: Meat & poultry, Confectionary & candy, Bakery; Container & packaging				
Main product feature	Anti-microbial, Foodg	Anti-microbial, Foodgrade, Non-fraying			
Belt construction					
Number of plies		1			
Top side	material	Ropanyl, TPU			
	finish	profile, A16 Nipple profile 1.5 mm			
	color	Light blue	Light blue		
	finish	profile			
<b>e</b>					
Characteristics					
Food Grade (FG)	yes	FDA			
Antistatic (AS)	no				
High conductive (HC)	no				
Flame-retardant (FR)	no				
ATEX approval	no				
Technical data					
Hardness	ISO 868	top side	93A Shore		
Force at 1% elongation (static)	ISO 21181	top side	6 N/mm	34.26 lbs/in.	
Thickness	AB method KV.002	total	2.5 mm	0.1 in.	
THICKNESS	Ab method KV.002	top cover	1.7 mm	0.07 in.	
Weight	AB method KV.004		1.75 kg/m <sup>2</sup>	0.36 lbs/ft <sup>2</sup>	
Operating temperature	continuous	from / to	-20 / 90 °C	-4 / 194 °F	
	short	from / to	-30 / 110 °C	-22 / 230 °F	
Minimum pulley diameter	flexing		-30 / 110 °C	0.59 in.	
	backflexing		30 mm	1.18 in.	
Manufacturing width	standard		2000 mm	78.74 in.	
Handracturing width	maximum		2000 mm	78.74 in.	
	maximum		2000 11111	70.74 III.	

## Fabrication

Hot splicing is always preferable. Glueing can only be done when the belt is exposed to normal temperature and the humidity is not excessive. For the working method, consult the splice information and the equipment literature. Apply the recommended splice as indicated in the seperate information.

## Additional information

This sheet contains typical values, which apply to a temperature of approx. 20 °C (68 °F), unless otherwise stated, individual data may differ. We recommend to keep the belt tension to a practical working minimum to maximize the service life of the belt and machine parts. Always protect belts from sunlight/UV-radiation, avoid temperatures below 10°C and above 40°C, dust and dirt. Store belts in a cool and dry place and if possible in their original packaging.

For details consult 'Storage and handling instructions' or contact our specialist.

Because of continuous development, the presented data is subject to alteration. This data replaces that included in previous publications. Ammeraal Beltech excludes any liability for the incorrect use of the above stated information. Subject to the general terms and conditions of sale and delivery, as applied by its operating companies, are all activities performed and services rendered by Ammeraal Beltech.