**Technical datasheet** 

## Ropanyl EM05 6/1 00+P29 white AS FG



Article code: SBRY579898

General information	
Product group	Synthetic Belts
Industry segment	Food: Confectionary & candy
Main product feature	Antistatic, Foodgrade, Laterally stable
Indication of use	Slider bed, Flat

Belt construction						
Tension layer		polyester, stable				
Number of plies		1				
Top side	material	Ropanyl, TPU				
	finish	profile, P29 Positive rhomboid profile				
	color	white				
Bottom side	material	Ropanol, PUR				
	finish	impregnated fabric				
	color	transparent				

Characteristics						
Food Grade (FG)	yes	EC 1935/2004, EU 10/2011; FDA				
Antistatic (AS)	yes	ISO 21178				
High conductive (HC)	no					
ATEX approval	no					

Technical data									
Hardness	ISO 868	top side	85A	Shore					
Force at 1% elongation (static)	ISO 21181		6	N/mm	34.26	lbs/in.			
Thickness	AB method KV.002	total	1.25	mm	0.05	in.			
		top cover	0.25	mm	0.01	in.			
Weight	AB method KV.004		1.4	kg/m²	0.29	lbs/ft²			
Operating temperature	continuous	from / to	-20 / 90	°C	-4 / 194	°F			
	short	from / to	-30 / 110	°C	-22 / 230	°F			
Minimum pulley diameter	flexing		10	mm	0.39	in.			
	backflexing		20	mm	0.79	in.			
Manufacturing width	standard		1600	mm	62.99	in.			
	maximum		1600	mm	62.99	in.			

## Fabrication

Hot splicing is always preferable. Glueing can only be done when the belt is exposed to normal temperature and the humidity is not excessive. For the working method, consult the splice information and the equipment literature. Apply the recommended splice as indicated in the seperate information.

## Additional information

This sheet contains typical values, which apply to a temperature of approx. 20  $^{\circ}$ C (68  $^{\circ}$ F), unless otherwise stated, individual data may differ.

We recommend to keep the belt tension to a practical working minimum to maximize the service life of the belt and machine parts.

Always protect belts from sunlight/UV-radiation, avoid temperatures below 10°C and above 40°C, dust and dirt. Store belts in a cool and dry place and if possible in their original packaging.

For details consult 'Storage and handling instructions' or contact our specialist.