Technical datasheet

PU Linear L Steel

Article code: TBPU000106




Afticle code: TBP0000106					
General information					
Productgroup	Timing belts, P	U Linear			
Industry segment	General industr	ry; Wood; Building m	aterials: Stone & ceramics,	Bricks & tiles	
Main product feature	Positive drive,	Wear resistant			
Belt construction					
Tension member		steel			
Material	body	Polyurethane			
Surface	tooth side	Polyurethane			
	back side	Polyurethane			
Characteristics					
Food Grade (FG)	no				
Antistatic (AS)	no				
Oil & Fat resistance	yes				
Technical data					
Tooth	profile			L	
	pitch			9.525 mm	0.37 in.
Hardness body material	ISO 868			92A Shore	
Belt thickness	total			3.6 mm	0.14 in.
Belt weight				3.9 kg/m ²	0.8 lbs/ft ³
Coefficient of friction	tooth side to st	eel	dynamic	0,5	
Operating temperature	continuous		from / to	-10 / 80 °C	14/176 °F
Minimum pulley diameter	A) without cour	iter flexing	number of teeth, t1	15	
			d1	44.72 mm	1.76 in.
			d2	60 mm	2.36 in.
	B) with counter	flexing	number of teeth, t1	20	
			d1	59.88 mm	2.36 in.
			d2	60 mm	2.36 in.
Belt width	maximum			101.6 mm	4 in.

Reference images

Manufacturing length

Endless length


Side view



minimum

standard

A) without counter flexing






500 mm

100000 mm

19.69 in.

328.08 ft.



Fabrication

This information on the fabrication options is general, please contact Ammeraal Beltech for the specific fabrication possibilities of the timing belt of your choice.

Open end, prepared splice, spliced endless with mechanical fastener or a pin joint fastener.

Cleats welded or mechanically attached, metal teeth, guides welded or glued.

Covers can be welded, glued, coated or vulkanized onto the back side of the timing belt.

Thermoplastic covers can be embossed. Perforations, lateral and logitudinal slots, lateral and longitudinal profiles.

Additional Information

Tooth profile according to standard: metric ISO 17396 , imperial ISO 5296-1, curvilinear ISO 13050, depending on the belt type.

This sheet contains typical values, which apply to a temperature of approx. 20 °C (68 °F), unless otherwise stated, individual data may differ. Consult our specialists for further information like technical calculations. Instructions regarding joining, storage & maintenance and tracking & tensioning.

Standard belt width [mm]	Allow. tensile load Linear open end & Torque [N]	Allow. tensile load Linear welded endless [N]	Spring force [N]
12.7	890	445	175000
19.1	1340	670	315000
25.4	1780	890	420000
38.1	2670	1335	630000
50.8	3560	1780	840000
76.2	5340	2670	1290000
101.61	7120	3560	1710000

Speed rpm [1/min]	Specific tooth force [N/mm]	Specific power [W/mm]
0	3.86	0
25	3.655	0.015
50	3.575	0.028
75	3.492	0.042
100	3.407	0.054
150	3.283	0.078
200	3.159	0.1
300	2.979	0.142
400	2.839	0.18
500	2.725	0.216
750	2.507	0.298
1000	2.344	0.372
1250	2.214	0.439
1500	2.107	0.502
1750	2.015	0.56
2000	1.935	0.614
3000	1.688	0.804
4000	1.509	0.958

Standard

Because of continuous development, the presented data is subject to alteration. This data replaces that included in previous publications. Ammeraal Beltech excludes any liability for the incorrect use of the above stated information. Subject to the general terms and conditions of sale and delivery, as applied by its operating companies, are all activities performed and services rendered by Ammeraal Beltech.