

# Teflon EC 10/5 01+01 (NI) black CR HR

Article code: LWTE560246

## General information

**Product group** Light Weight Rubber

## Belt construction

<b>Tension layer</b>		polyester, stable
<b>Number of plies</b>		5
<b>Top side</b>	<b>material</b>	Teflon, TE
	<b>finish</b>	smooth
	<b>color</b>	black
<b>Bottom side</b>	<b>material</b>	Nitrile, TE
	<b>finish</b>	smooth
	<b>color</b>	black

## Characteristics

<b>Food Grade (FG)</b>	no
<b>Antistatic (AS)</b>	no

## Technical data

<b>Force at 1% elongation</b>	ISO 21181		10 N/mm	57.1 lbs/in.
<b>Thickness</b>	AB method KV.002	belt	5.6 mm	0.22 in.
		top cover	0.1 mm	0 in.
<b>Weight</b>	AB method KV.004		6.3 kg/m <sup>2</sup>	1.29 lbs/ft <sup>2</sup>
<b>Operating temperature</b>	continuous	from / to	-18 / 121 °C	-0.4 / 249.8 °F
	short	from / to	-18 / 121 °C	-0.4 / 249.8 °F
<b>Minimum pulley diameter</b>	flexing		102 mm	4.02 in.
	backflexing		102 mm	4.02 in.
<b>Manufacturing width</b>	standard		1524 mm	60 in.
	maximum		1524 mm	60 in.

## Fabrication

Vulcanizing is always preferable. Cold splicing can only be done when the belt is exposed to normal temperature and the humidity is not excessive. For the working method, consult the splice information and the equipment literature. Apply the recommended splice as indicated in the separate information.

## Additional information

This sheet contains typical values, which apply to a temperature of approx. 20 °C (68 °F), unless otherwise stated, individual data may differ.

We recommend to keep the belt tension to a practical working minimum to maximize the service life of the belt and machine parts.

Always protect belts from sunlight/UV-radiation, avoid temperatures below 10°C and above 40°C, dust and dirt. Store belts in a cool and dry place and if possible in their original packaging.

For details consult 'Storage and handling instructions' or contact our specialist.