Technical datasheet

# PU Linear 100 ATK5-6 Steel




Article code: TBPU000155

General information							
Productgroup	Timing belts, PU L	_inear					
Industry segment	General industry;	Container & pack	aging; Paper & print				
Main product feature	Positive drive, Sel	lf-alignment, Wea	r resistant				
Belt construction							
Tension member		steel					
Material	body	Polyurethan	e				
Surface	tooth side	Polyurethan	e				
	back side	Polyurethan	e				
Characteristics							
Food Grade (FG)	no						
Antistatic (AS)	no						
Oil & Fat resistance	good						
Technical data							
Tooth	profile			AT5			
	pitch			5	mm	0.2	in.
Hardness body material	ISO 868			92A	Shore		
Belt thickness				2.7	mm	0.11	in.
Coefficient of friction	tooth side to stee	I	dynamic	0,5			
			static	0,6			
Operating temperature	continuous		from / to	-10 / 80	°C	14 / 176	°F
Minimum pulley diameter	A) without counte	er flexing	number of teeth, t1	25			
			14	20 50		4 50	


operating temperature	continuous	1101117 20	10,00	C	11, 1,0	•
Minimum pulley diameter	A) without counter flexing	number of teeth, t1	25			
		d1	38.56	mm	1.52	in.
		d2	60	mm	2.36	in.
	B) with counter flexing	number of teeth, t1	25			
		d1	38.56	mm	1.52	in.
		d2	80	mm	3.15	in.
Belt width			100	mm	3.94	in.
Endless length	minimum		500	mm	19.69	in.
Manufacturing length	standard		100000	mm	328.08	ft.

#### **Reference images**

A) without counter flexing



## B) with counter flexing



### Fabrication

This information on the fabrication options is general, please contact Ammeraal Beltech for the specific fabrication possibilities of the timing belt of your choice.

Open end, prepared splice, spliced endless with mechanical fastener or a pin joint fastener.

Cleats welded or mechanically attached, metal teeth, guides welded or glued.

Covers can be welded, glued, coated or vulkanized onto the back side of the timing belt.

Thermoplastic covers can be embossed. Perforations, lateral and logitudinal slots, lateral and longitudinal profiles.

## Additional Information

Tooth profile according to standard: metric ISO 17396, imperial ISO 5296-1, curvilinear ISO 13050, depending on the belt type. This sheet contains typical values, which apply to a temperature of approx. 20 °C (68 °F), unless otherwise stated, individual data may differ. Consult our specialists for further information like technical calculations. Instructions regarding joining, storage & maintenance and tracking & tensioning.

Standard belt width [mm]	Allow. tensile load Linear open end & Torque [N]	Allow. tensile load Linear welded endless [N]	Spring force [N]
10	560	280	140000
16	1100	550	280000
25	1700	850	437500
32	2220	1110	560000
50	3500	1750	875000
75	5250	2625	1312500
100.1	7000	3500	1750000

		o
Speed rpm [1/min]	Specific tooth force [N/mm]	Specific power [W/mm]
0	3.64	0
25	3.572	0.007
50	3.501	0.015
75	3.468	0.022
100	3.424	0.029
150	3.34	0.042
200	3.292	0.055
300	3.192	0.08
400	3.089	0.103
500	2.995	0.125
750	2.807	0.175
1000	2.649	0.221
1250	2.522	0.263
1500	2.416	0.302
1750	2.326	0.339
2000	2.242	0.374
3000	1.985	0.496
4000	1.796	0.599

Standard

Because of continuous development, the presented data is subject to alteration. This data replaces that included in previous publications. Ammeraal Beltech excludes any liability for the incorrect use of the above stated information. Subject to the general terms and conditions of sale and delivery, as applied by its operating companies, are all activities performed and services rendered by Ammeraal Beltech.