Technical datasheet

Flexam ESM 6/2 0+A18 black AS

Article code: SBFL589760



General information	
Product group	Synthetic Belts
Industry segment	Logistics
Main product feature	Antistatic
Indication of use	Flat, Rollers, Slider bed

Belt construction						
Tension layer		polyester spun, stable				
Number of plies		2				
Top side	material	Flexam, PVC				
	finish	profile, A18 Fine square profile				
	color	black				
Bottom side	material	fabric, polyester spun				
	finish	bare fabric				
	color	natural				

Characteristics		
Food Grade (FG)	no	
Antistatic (AS)	yes	ISO 21178
High conductive (HC)	no	
Flame-retardant	no	
	yes	ASTM D-378
ATEX approval	no	

Technical data								
Hardness	ISO 868	top side	55A	Shore				
Force at 1% elongation (static)	ISO 21181		6	N/mm	34.26	lbs/in.		
Thickness	AB method KV.002	total	2.00	mm	0.08	in.		
		top cover	0.70	mm	0.03	in.		
Weight	AB method KV.004		1.9	kg/m²	0.39	lbs/ft²		
Operating temperature	continuous	from / to	-10 / 80	°C	14 / 176	°F		
	short	from / to	-10 / 100	°C	14 / 212	°F		
Minimum pulley diameter	flexing		25	mm	0.98	in.		
	backflexing		40	mm	1.57	in.		
Manufacturing width	standard		2000	mm	78.74	in.		
	maximum		3000	mm	118.11	in.		

Fabrication

Hot splicing is always preferable. Glueing can only be done when the belt is exposed to normal temperature and the humidity is not excessive. For the working method, consult the splice information and the equipment literature. Apply the recommended splice as indicated in the seperate information.

Additional information

This sheet contains typical values, which apply to a temperature of approx. 20 °C (68 °F), unless otherwise stated, individual data may differ.

We recommend to keep the belt tension to a practical working minimum to maximize the service life of the belt and machine parts.

Always protect belts from sunlight/UV-radiation, avoid temperatures below 10°C and above 40°C, dust and dirt. Store belts in a cool and dry place and if possible in their original packaging.

For details consult 'Storage and handling instructions' or contact our specialist.