**Technical datasheet** 

## Ropanyl EM05 10/2 00+03 petrol M1 AS FG NL



## Article code: SBRY513259

General information						
Product group	Synthetic Belts	Synthetic Belts				
Main product feature	Antistatic, Foodgrade					
Indication of use	Flat, Rollers, Slider bed	Flat, Rollers, Slider bed				
Belt construction						
Tension layer		polyester, extra stable				
Number of plies		2				
Top side	material	Ropanyl, TPU	Ropanyl, TPU			
	finish	smooth, M1 Fin	smooth, M1 Fine matt finish			
	color	petrol	petrol			
Bottom side	material	Ropanol, TPU	Ropanol, TPU			
	finish	impregnated fa	impregnated fabric			
	color	transparent	transparent			
Characteristics						
Food Grade (FG)	yes	FDA				
Antistatic (AS)	yes	ISO 21178				
High conductive (HC)	no					
Flame-retardant (FR)	no					
ATEX approval	no					
Technical data	100.000	have all to	OFA Chan			
Hardness	ISO 868	top side	85A Shore		lle e llee	
Force at 1% elongation (static)	ISO 21181	ha ha l	10 N/mr		lbs/in.	
Thickness	AB method KV.002	total	2.30 mm	0.09		
144 - 1 - 1 - 1 - 1		top cover	0.40 mm	0.02		
Weight	AB method KV.004	for any 1 he	2.9 kg/m		lbs/ft <sup>2</sup>	
Operating temperature	continuous	from / to	-30 / 90 °C	-22 / 194		
	short	from / to	-30 / 110 °C	-22 / 230		
Minimum pulley diameter	flexing		50 mm	1.97		
	backflexing		90 mm	3.54		
Manufacturing width	standard		2000 mm	78.74		
	maximum		2000 mm	78.74	in.	

## Fabrication

Hot splicing is always preferable. Glueing can only be done when the belt is exposed to normal temperature and the humidity is not excessive. For the working method, consult the splice information and the equipment literature. Apply the recommended splice as indicated in the seperate information.

## **Additional information**

This sheet contains typical values, which apply to a temperature of approx. 20 °C (68 °F), unless otherwise stated, individual data may differ.

We recommend to keep the belt tension to a practical working minimum to maximize the service life of the belt and machine parts.

Always protect belts from sunlight/UV-radiation, avoid temperatures below 10°C and above 40°C, dust and dirt. Store belts in a cool and dry place and if possible in their original packaging.

For details consult 'Storage and handling instructions' or contact our specialist.

Because of continuous development, the presented data is subject to alteration. This data replaces that included in previous publications. Ammeraal Beltech excludes any liability for the incorrect use of the above stated information. Subject to the general terms and conditions of sale and delivery, as applied by its operating companies, are all activities performed and services rendered by Ammeraal Beltech.