## **Endless Woven K84XSBP AmDough80XS Cotton 2.4mm**



Article code: RMFA000051

All title couci Ki ii Alooobii								
General information								
Product group	endless woven	endless woven						
Industry segment	Food: Bakery	Food: Bakery						
Main product feature	Foodgrade, Mois	Foodgrade, Moisture absorbant, Non-fraying						
Application	Rotary moulder	Rotary moulder belt, Rotary cutter, Oven infeed belt						
Indication of use	Knife edge trans	Knife edge transfer, Abrasive applications						
Belt construction								
Tension layer		Twill, cotton-polyamide						
Number of plies		1						
Bottom side	material	Ropanol, PUR						
	finish	finish impregnation						
		transparent						
Characteristics								
			05 /000 / 5U / 000 / 4					
Food Grade (FG)	yes	EC 1935/2004, EU 10-2011; FDA						
Technical data								
Tensile Strength	ISO 21181			120	N/mm	685.22	lbs/in.	
Thickness			total	2.4	mm	0.09	in.	
Weight				1.5	kg/m²	0.31	lbs/ft²	
Length			min. / max.	800 / 52000	mm	31.5 / 2047.24	in.	
Width			min. / max.	40 / 3400	mm	1.57 / 133.86	in.	
Operating temperature	continuous		from / to	-10 / 90	°C	14 / 194	°F	
	short		from / to	-30 / 110	°C	-22 / 230	°F	
Minimum pulley diameter				4	mm	0.16	in.	
Tolerances								
Length	± 2 %		minimum ±	20	mm	0.79	in.	
Width	± 2 %		minimum ±	2	mm	0.08	in.	
Thickness			±	0.5	mm	0.02	in.	

<b>Process and Conveyor</b>	Belt

## Top view



Belttype	Material	Weave	Belt Thickness [mm]
AmDough 100	cotton	broken twill	2.8
AmDough 90	cotton	broken twill	2.4
AmDough 80	cotton / polyamide	broken twill	2.4
AmDough 70	cotton	plain	2.0
AmDough 60	cotton / polyamide	broken twill	2.4
AmDough 50	cotton / polyamide	plain	1.8
AmDough 40	cotton / polyamide	plain	2.0
AmDough 20	cotton / polyester	plain	2.0

There is a linear relationship between the AmDough absorption numbers:

Heavy dough: wet, high degree of moisture, AmDough belt with higher absorption factor

Light dough: dry, low degree of moisture, AmDough belt with lower absorption factor

Top side: always uncoated

Bottom side: PUR transparent food grade impregnation for stability, better wear resistance and longer belt life

Belt edges are reinforced with polyamide selvedges.

Dimension: length up to 100 m, width up to 3400 mm

Broken twill (GK) types are also available as Twill (k) versions.

## **Additional information**

This sheet contains typical values, which apply to a temperature of approx. 20 °C (68 °F), unless otherwise stated, individual data may differ.

Diameter of knife edge <135° [mm]
5
4
4
3
4
3
3
3