

**Fabric E郑/C 10/1 0+0 (NI) white CR FG HR**

Article code: ZLFA560203

**General information**

|                             |                                           |
|-----------------------------|-------------------------------------------|
| <b>Product group</b>        | Ziplink                                   |
| <b>Industry segment</b>     | Food: Bakery                              |
| <b>Main product feature</b> | Cold resistant, Foodgrade, Heat resistant |
| <b>Indication of use</b>    | Slider bed, Rollers, Flat                 |

**Belt construction**

|                        |                 |                          |
|------------------------|-----------------|--------------------------|
| <b>Tension layer</b>   |                 | Ziplink fabric, flexible |
| <b>Number of plies</b> |                 | 1                        |
| <b>Top side</b>        | <b>material</b> | fabric, cotton/polyester |
|                        | <b>finish</b>   | bare                     |
|                        | <b>color</b>    | natural                  |
| <b>Bottom side</b>     | <b>material</b> | Mesh, polyester          |
|                        | <b>finish</b>   | bare                     |
|                        | <b>color</b>    | white                    |

**Characteristics**

|                        |     |     |
|------------------------|-----|-----|
| <b>Food Grade (FG)</b> | yes | FDA |
|------------------------|-----|-----|

**Technical data**

|                               |                  |           |                        |                          |
|-------------------------------|------------------|-----------|------------------------|--------------------------|
| <b>Force at 1% elongation</b> | ISO 21181        |           | 10 N/mm                | 57.1 lbs/in.             |
| <b>Thickness</b>              | AB method KV.002 |           | 3.05 mm                | 0.12 in.                 |
|                               |                  | top cover | 0 mm                   | 0 in.                    |
| <b>Weight</b>                 | AB method KV.004 |           | 3.71 kg/m <sup>2</sup> | 0.76 lbs/ft <sup>2</sup> |
| <b>Operating temperature</b>  | continuous       | from / to | 0 / 121 °C             | 32 / 249.8 °F            |
| <b>Manufacturing width</b>    | standard         |           | 1829 mm                | 72.01 in.                |
|                               | maximum          |           | 1829 mm                | 72.01 in.                |

**Fabrication**

Ziplink belts can be endless, very easy and quick splicing without presses, fasteners or glues. Refer to the technical information for more information about splicing of Ziplink belts.

**Additional information**

This sheet contains typical values, which apply to a temperature of approx. 20 °C (68 °F), unless otherwise stated, individual data may differ.

We recommend to keep the belt tension to a practical working minimum to maximize the service life of the belt and machine parts.

Always protect belts from sunlight/UV-radiation, avoid temperatures below 10°C and above 40°C, dust and dirt. Store belts in a cool and dry place and if possible in their original packaging.

For details consult 'Storage and handling instructions' or contact our specialist.

Because of continuous development, the presented data is subject to alteration. This data replaces that included in previous publications. Ammeraal Beltech excludes any liability for the incorrect use of the above stated information. Subject to the general terms and conditions of sale and delivery, as applied by its operating companies, are all activities performed and services rendered by Ammeraal Beltech.