Technical datasheet

Ropanyl EM 3/1 00+02 dark green M2 AS FG



Article code: SBRY572251

General information							
Product group	Synthetic Belts	Synthetic Belts					
Industry segment	Agriculture: Horticultu	Agriculture: Horticulture; Container & packaging					
Main product feature	Antistatic, Foodgrade	Antistatic, Foodgrade					
Indication of use	Slider bed, Flat	Slider bed, Flat					
Belt construction							
Tension layer		polyester, stable					
Number of plies		1					
Top side	material						
	finish						
	color	dark green	-				
Bottom side	material	Ropanol, PUR					
	finish		impregnated fabric				
	color	natural					
Characteristics							
Food Grade (FG)	Ves	yes EC 1935/2004, EU 10/2011; FDA					
Antistatic (AS)	-	yes ISO 21178					
High conductive (HC)	no	100 211/0					
Flame-retardant (FR)	no						
ATEX approval	no						
Technical data							
Hardness	ISO 868	top side	93A	Shore			
Force at 1% elongation (static)	ISO 21181		3	N/mm	17.13	lbs/in.	
Thickness	AB method KV.002	total	0.80	mm	0.03	in.	
		top cover	0.20	mm	0.01	in.	
Weight	AB method KV.004		0.8	kg/m²	0.16	lbs/ft²	
Operating temperature	continuous	from / to	-20 / 90	°C	-4 / 194	°F	
	short	from / to	-30 / 110	°C	-22 / 230	°F	
Minimum pulley diameter	flexing		8	mm	0.31	in.	
	backflexing		10	mm	0.39	in.	
			2020		70.50		

Fabrication

Hot splicing is always preferable. Glueing can only be done when the belt is exposed to normal temperature and the humidity is not excessive. For the working method, consult the splice information and the equipment literature. Apply the recommended splice as indicated in the seperate information.

2020 mm

2040 mm

79.53 in.

80.31 in.

Additional information

Manufacturing width

This sheet contains typical values, which apply to a temperature of approx. 20 °C (68 °F), unless otherwise stated, individual data may differ. We recommend to keep the belt tension to a practical working minimum to maximize the service life of the belt and machine parts. Always protect belts from sunlight/UV-radiation, avoid temperatures below 10°C and above 40°C, dust and dirt. Store belts in a cool and dry place and if possible in their original packaging.

For details consult 'Storage and handling instructions' or contact our specialist.

standard

maximum

Because of continuous development, the presented data is subject to alteration. This data replaces that included in previous publications. Ammeraal Beltech excludes any liability for the incorrect use of the above stated information. Subject to the general terms and conditions of sale and delivery, as applied by its operating companies, are all activities performed and services rendered by Ammeraal Beltech.