

# Endless Woven P3083B AmDough50 Cotton 1.8mmCMM254

Article code: RMFA000130

## General information

<b>Product group</b>	endless woven
<b>Industry segment</b>	Food: Bakery
<b>Main product feature</b>	Foodgrade, Moisture absorbant, Non-fraying
<b>Application</b>	Rotary moulder belt, Rotary cutter, Oven infeed belt
<b>Indication of use</b>	Knife edge transfer, Abrasive applications

## Belt construction

<b>Tension layer</b>		Plain, cotton
<b>Number of plies</b>		1
<b>Bottom side</b>	<b>material</b>	Ropanol, PUR
	<b>finish</b>	impregnation
		transparent

## Characteristics

<b>Food Grade (FG)</b>	yes	EC 1935/2004, EU 10-2011; FDA
------------------------	-----	-------------------------------

## Technical data

<b>Tensile Strength</b>	ISO 21181		90 N/mm	513.91 lbs/in.
<b>Thickness</b>		total	1.8 mm	0.07 in.
<b>Weight</b>			1.3 kg/m <sup>2</sup>	0.27 lbs/ft <sup>2</sup>
<b>Length</b>		min. / max.	800 / 52000 mm	31.5 / 2047.24 in.
<b>Width</b>		min. / max.	40 / 3400 mm	1.57 / 133.86 in.
<b>Operating temperature</b>	continuous	from / to	-10 / 130 °C	14 / 266 °F
	short	from / to	-30 / 150 °C	-22 / 302 °F
<b>Minimum pulley diameter</b>			3 mm	0.12 in.

## Tolerances

<b>Length</b>	± 2 %	minimum ±	20 mm	0.79 in.
<b>Width</b>	± 2 %	minimum ±	2 mm	0.08 in.
<b>Thickness</b>		±	0.5 mm	0.02 in.



## Top view



## Standard AmDough range

Beltype	Material	Weave	Belt Thickness [mm]
AmDough 100	cotton	broken twill	2.8
AmDough 90	cotton	broken twill	2.4
AmDough 80	cotton / polyamide	broken twill	2.4
AmDough 70	cotton	plain	2.0
AmDough 60	cotton / polyamide	broken twill	2.4
AmDough 50	cotton / polyamide	plain	1.8
AmDough 40	cotton / polyamide	plain	2.0
AmDough 20	cotton / polyester	plain	2.0

There is a linear relationship between the AmDough absorption numbers:

Heavy dough: wet, high degree of moisture, AmDough belt with higher absorption factor

Light dough: dry, low degree of moisture, AmDough belt with lower absorption factor

Top side: always uncoated

Bottom side: PUR transparent food grade impregnation for stability, better wear resistance and longer belt life

Belt edges are reinforced with polyamide selvedges.

Dimension: length up to 100 m, width up to 3400 mm

Broken twill (GK) types are also available as Twill (k) versions.

## Additional information

This sheet contains typical values, which apply to a temperature of approx. 20 °C (68 °F), unless otherwise stated, individual data may differ.

Diameter of knife edge <135° [mm]
5
4
4
3
4
3
3
3