Technical datasheet

## Nonex EM 15/3 A18+07 light blue FG

Article code: SBN0887202



General information	
Product group	Synthetic Belts
Industry segment	Food
Main product feature	Foodgrade, Oil & grease resistant
Indication of use	Flat, Rollers, Slider bed

**Belt construction** 

Tension layer		polyester, stable
Number of plies		3
Top side	material	Nonex, PVC
	finish	smooth, glossy
	color	Light blue
Bottom side	material	Nonex, PVC
	finish	profile, A18 Fine square profile
	color	Light blue
Characteristics		

Food Grade (FG)	yes	FDA	
Antistatic (AS)	no		
High conductive (HC)	no		
Flame-retardant (FR)	no		
ATEX approval	no		

Technical data						
Hardness	ISO 868	top side	70A	Shore		
Force at 1% elongation (static)	ISO 21181		15	N/mm	85.65	lbs/in.
Thickness	AB method KV.002	total	4.2	mm	0.17	in.
		top cover	0.7	mm	0.03	in.
Weight	AB method KV.004		4.5	kg/m²	0.92	lbs/ft²
Operating temperature	continuous	from / to	-15 / 80	°C	5 / 176	°F
	short	from / to	-15 / 100	°C	5 / 212	°F
Minimum pulley diameter	flexing		110	mm	4.33	in.
	backflexing		160	mm	6.3	in.
Manufacturing width	standard		3000	mm	118.11	in.
	maximum		3000	mm	118.11	in.

## Fabrication

Hot splicing is always preferable. Glueing can only be done when the belt is exposed to normal temperature and the humidity is not excessive. For the working method, consult the splice information and the equipment literature. Apply the recommended splice as indicated in the seperate information.

## **Additional information**

This sheet contains typical values, which apply to a temperature of approx. 20 °C (68 °F), unless otherwise stated, individual data may differ. We recommend to keep the belt tension to a practical working minimum to maximize the service life of the belt and machine parts. Always protect belts from sunlight/UV-radiation, avoid temperatures below 10°C and above 40°C, dust and dirt. Store belts in a cool and dry place and if possible in their original packaging.

For details consult 'Storage and handling instructions' or contact our specialist.

Because of continuous development, the presented data is subject to alteration. This data replaces that included in previous publications. Ammeraal Beltech excludes any liability for the incorrect use of the above stated information. Subject to the general terms and conditions of sale and delivery, as applied by its operating companies, are all activities performed and services rendered by Ammeraal Beltech.