

Cotton - 40 - 2ply - ST weave

Article code: SBCO012840

General information

Product group Synthetic Belts

Belt construction

Number of plies		2
Top side	material	fabric, cotton
	finish	bare fabric
	color	natural
Bottom side	material	fabric, cotton
	finish	bare fabric
	color	natural

Characteristics

Food Grade (FG)	no
Antistatic (AS)	no
High conductive (HC)	no
Flame-retardant (FR)	no
ATEX approval	no

Technical data

Thickness	AB method KV.002	total	2.4 mm	0.09 in.
Weight	AB method KV.004		1.56 kg/m ²	0.32 lbs/ft ²
Minimum pulley diameter	flexing		25 mm	0.98 in.
	backflexing		25 mm	0.98 in.
Manufacturing width	standard		1016 mm	40 in.
	maximum		1016 mm	40 in.

Fabrication

Hot splicing is always preferable. Glueing can only be done when the belt is exposed to normal temperature and the humidity is not excessive. For the working method, consult the splice information and the equipment literature. Apply the recommended splice as indicated in the separate information.

Additional information

This sheet contains typical values, which apply to a temperature of approx. 20 °C (68 °F), unless otherwise stated, individual data may differ.

We recommend to keep the belt tension to a practical working minimum to maximize the service life of the belt and machine parts.

Always protect belts from sunlight/UV-radiation, avoid temperatures below 10°C and above 40°C, dust and dirt. Store belts in a cool and dry place and if possible in their original packaging.

For details consult 'Storage and handling instructions' or contact our specialist.

Because of continuous development, the presented data is subject to alteration. This data replaces that included in previous publications. Ammeraal Beltech excludes any liability for the incorrect use of the above stated information. Subject to the general terms and conditions of sale and delivery, as applied by its operating companies, are all activities performed and services rendered by Ammeraal Beltech.