Technical datasheet

Flexam EF 30/2 01+A34 green



Article code: SBFL571342

General information							
Product group	Synthetic Belts	Synthetic Belts					
Industry segment	Paper & print	Paper & print					
Indication of use	Rollers, Flat, Troughe	Rollers, Flat, Troughed					
Belt construction							
Tension layer		polyester, flex	polyester, flexible				
Number of plies		2	2				
Top side	material	material Flexam, PVC					
	finish	finish profile, A34 Supergrip profile					
	color						
Bottom side	material	terial Flexam, PVC					
	finish	finish impregnated fabric					
	color	green	green				
a							
Characteristics							
Food Grade (FG)	no						
Antistatic (AS)	no						
High conductive (HC)	no						
Flame-retardant (FR)	no						
ATEX approval	no						
Technical data							
Hardness	ISO 868	top side	55A	Shore			
Force at 1% elongation (static)	ISO 21181		30	N/mm	171.3	lbs/in.	
Thickness	AB method KV.002	total	6.1	mm	0.24	in.	
		top cover	3.2	mm	0.13	in.	
Weight	AB method KV.004		5.1	kg/m²	1.04	lbs/ft²	
Operating temperature	continuous	from / to	-15 / 80	°C	5 / 176	°F	
	short	from / to	-15 / 100	°C	5 / 212	°F	
Minimum pulley diameter	flexing		120	mm	4.72	in.	
	backflexing		240	mm	9.45	in.	
Manufacturing width	standard		2050	mm	80.71	in.	
	maximum		2040	mm	80.31	in.	

Fabrication

Hot splicing is always preferable. Glueing can only be done when the belt is exposed to normal temperature and the humidity is not excessive. For the working method, consult the splice information and the equipment literature. Apply the recommended splice as indicated in the seperate information.

Additional information

This sheet contains typical values, which apply to a temperature of approx. 20 °C (68 °F), unless otherwise stated, individual data may differ.

We recommend to keep the belt tension to a practical working minimum to maximize the service life of the belt and machine parts.

Always protect belts from sunlight/UV-radiation, avoid temperatures below 10°C and above 40°C, dust and dirt. Store belts in a cool and dry place and if possible in their original packaging.

For details consult 'Storage and handling instructions' or contact our specialist.

Because of continuous development, the presented data is subject to alteration. This data replaces that included in previous publications. Ammeraal Beltech excludes any liability for the incorrect use of the above stated information. Subject to the general terms and conditions of sale and delivery, as applied by its operating companies, are all activities performed and services rendered by Ammeraal Beltech.